



# FICHA TÉCNICA DE PRODUCTO

## TECHNICAL DATA SHEET

**Ref. 4.8100.000**

### **Adhesivo para Fibra (5 ml)** **Fiberglass Adhesive (5 ml)**



Color <i>Colour</i>	Verde / Green
Uniones roscadas a partir de <i>For threaded joints up to</i>	M20 R 3/4"
Viscosidad a +25°C (+77°F) <i>Viscosity at +25°C (+77°F) Brookfield</i>	700 - 1.000 mPa·s
Capacidad max. p/rellenar huecos <i>Gap filling capacity max.</i>	0,15 mm
Fuerza de rotura <i>Breakaway strength (Thread)</i>	30-35 Nm
Fuerza prevaliente <i>Prevailing strength (Thread)</i>	55 -70 Nm
Esfuerzo de cizalla <i>Shear strength (DIN 54452)</i>	25 - 35 N/mm <sup>2</sup> (3.625 -5.075 psi)
Tiempo manipulado a temperatura ambiente <i>Handling strength at room temperature</i>	2 - 5 min.
Tiempo en alcanzar esfuerzo final a temperatura ambiente <i>Final strength at room temperature</i>	2 - 4 h
Rango de temperatura <i>Temperature range</i>	-60 up to + 180°C (-76 up to +356°F)

Revisión / Review : 10/02/2016

ESTIARE S.A.  
Pol.Ind. Cova Solera  
C/ Praga, 5  
08191 Rubí  
Barcelona - España

Tel. 935 861 282  
info@estiare.es  
www.estiare.com